

Thermal Properties

www.E-Crete.com

Table 13.0: Specific Heat (s) and Heat Capacity (HC) for AAC, brick veneer and ½" glued drywall

AAC Type	Density pcf	Specific Heat	Heat Capacity			
			Thickness, in.			
			6	8	10	12
AAC 2.5 (AAC2)	26	0.25	12.79	13.88	14.96	16.04
AAC 2.5 (AAC3)	32	0.25	13.54	14.88	16.21	17.54
AAC 5.0 (AAC5)	38	0.25	14.29	15.88	17.46	19.04
AAC 7.5 (AAC6)	44	0.25	15.04	16.88	18.71	20.54

Brick 4" • Density = 135 pcf, • Specific heat = 0.20 Btu/lb.°F

(*) "Thermal Performance For AAC Block-Residential Application" was prepared by Hebel and is the property of Autoclaved Aerated Concrete Product Association (AACPA) and is only to be used by members of the AACPA.